

Technical Data Sheet

Platinum Series
Hanley Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Bone Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<20	<25
Revere Pewter Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Slate Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
White Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<20	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-5/8"	2-1/4"	7-5/8"	4.0	525	6.86